

SLIPGrip®

Anti Slip Deck Coating



DESIGN

SUPPLY

FABRICATE

INSTALL



FIBREGRID

Our SlipGrip® Deck Coating is easy to apply and will significantly reduce the slip potential of decking and other underfoot timber products. Dries to a gritty finish to keep people on their feet.

SlipGrip® Deck Coating is a urethane alkyd-based resin thinned with white spirit. Contains aluminium oxide aggregate.

CHARACTERISTICS

- Prolongs decking lifespan
- Anti slip texture
- UV and fading resistant
- Chemical resistance
- Easy application with roller or brush
- Crack resistant due to flexibility
- Abrasion resistant
- Touch dry in 2-4 hours
- Can be recoated in 8 hours
- Aesthetically pleasing
- PTV 61 Dry, 52 Wet (low slip potential)

SUITABLE APPLICATIONS

- ✓ Public and private decking installations.

TECHNICAL DATA

Tin Size:	5 Litres
Coverage:	Approximately 40m ² (with 2 coats)
Coat Amount:	2 Coats is recommended
Colour:	Clear with a matte finish
Shelf Life:	At least a year if unopened
VOC:	EU limit for this product (cat A/i): 600g/l (2007)/500g/l (2010). This product contains 423g/l VOC. If in doubt, call us on 01440 712722

SLIP RESISTANCE VALUES

Measured using the Pendulum test method (WF rubber slider) - certificate available on request.

Top Surface	Dry Reading	Wet Reading
Coarse Grit	61	52

To ensure that the above slip resistance levels are maintained, the stair treads should be kept clean.




The UK Slip Resistance Group guide to slip resistance of a floor for able bodied pedestrians:

Four S Pendulum Value	Potential for Slip
Above 65	Extremely Low
35 - 65	Low
25 - 35	Moderate
25 & Below	High

PREPARATION

- ✓ Ensure the surface is clean, dry, and free from wax, oil, food residue or any other substance likely to affect the application of the coating. No primer is required.
- ✓ SlipGrip® Deck Coating relies on penetrating into the wood. If you aren't sure whether your wood has been sealed (which means the SlipGrip® Deck Coating might not stick to the deck), we recommend you pour a little drop of water on the deck. If it forms into droplets rather than in a pool, you will need to sand the deck lightly to make a key for the coating to adhere to the wood.
- ✓ Patch test a very small area to ensure you are happy with the appearance and that the product has been applied successfully.

APPLICATION

1. 	Give the mixture a good stir then use our 12" Roller to apply SlipGrip® Deck Coating.
2. 	Fill in hard to reach areas with our 5" Paint Brush.
3. 	Drying time is 2 - 4 hours, depending on weather conditions. If you need to apply a second coat, wait at least 8 hours for the first coat to properly cure before applying your second coat. Drying times are based on a substrate temperature of 20°C. Lower temperatures will prolong drying and recoating times. Do not apply to a damp surface, or when rain or frost is likely before SlipGrip® Deck Coating has completely dried. Wood must be totally dry before application. Recommended working temperature is 10°C.

CLEANING GUIDE & TIPS

Brushes and rollers should be cleaned with white spirit, which can also be used to treat spills.

HANDLING & STORAGE

Safe handling practices should always be employed and the appropriate Personal Protection Equipment is to be worn. Store in a safe place away from children. Suitable gloves should be worn. Only apply to areas that are well-ventilated.

If swallowed, seek urgent medical advice and show the practitioner the label.

Contains cobalt salt. May produce an allergic reaction. Keep out of reach from children.

Don't pour any residue into the drains or open water courses. Refer to safety data sheets. Dispose of at a suitable waste disposal centre. Wear suitable gloves. Use only in well-ventilated areas.

PERSONAL PROTECTION EQUIPMENT

Suitable gloves should be worn.



These installation instructions are to be used as a guide. Always employ safe practices. It is recommended to first test the suitability of any product on a small area before carrying out a full application.



Southern Office:
Unit 2, Civic Industrial Estate,
Homefield Road Central,
Haverhill,
Suffolk,
CB9 8QP



Northern Office:
Kingston House,
3 Walton Road,
Pattinson North,
Washington,
Tyne & Wear,
NE38 8QA



www.fibregrid.com



Email: sales@fibregrid.com



Phone: 01440 712722



001